

| Dodatek cementu | Siła I [kN] po 7 dniach | | | |
|--------------------|-------------------------|----------|----------|----------|
| | Próbka 1 | Próbka 2 | Próbka 3 | Próbka 4 |
| 3 | 5,569 | 4,368 | 5,306 | 3,962 |
| 5 | 7,698 | 5,458 | 6,987 | 6,654 |
| 7 | 10,597 | 9,632 | 10,941 | 9,284 |
| 9 | 15,521 | 14,691 | 15,757 | 14,445 |
| 11 | 22,89 | 24,236 | 24,974 | 25,514 |

| Dodatek cementu | Siła II [kN] po 7 dniach | | | |
|--------------------|--------------------------|----------|----------|----------|
| | Próbka 1 | Próbka 2 | Próbka 3 | Próbka 4 |
| 4 | 6,521 | 5,236 | 6,123 | 6,123 |
| 6 | 8,698 | 6,458 | 7,987 | 7,654 |
| 8 | 11,597 | 10,855 | 10,751 | 10,789 |
| 10 | 16,521 | 15,781 | 16,523 | 15,415 |
| 12 | 26,445 | 27,75 | 26,573 | 25,606 |

| Dodatek cementu | Siła III [kN] po 7 dniach | | | |
|--------------------|---------------------------|----------|----------|----------|
| | Próbka 1 | Próbka 2 | Próbka 3 | Próbka 4 |
| 5 | 7,569 | 6,368 | 5,306 | 5,962 |
| 6 | 8,698 | 8,458 | 7,987 | 8,654 |
| 7 | 9,827 | 9,544 | 9,668 | 9,346 |
| 8 | 11,956 | 11,632 | 11,349 | 12,038 |
| 9 | 15,085 | 14,728 | 14,035 | 14,734 |